

Chemical Resistance

GEHR PSU



	conc. (%)	room temperature	60 °C
1,4 Dioxane	100		
2-Hydroxypropionic acid	90		
Acetic acid	100	+	+
Acetone	100	-	-
Ammonia	conc.	o	
Ammonium chloride			
Amyl alcohol			
Apple juice			
Benzene		-	-
Bleaching solution	12,5 Cl		
Boric acid	100		
Brake fluid			
Butyl acetate		+	+
Calcium chloride		+	+
Carbon disulphide	100		
Carbon tetrachloride		o	-
Chlorine, gas	100		
Chlorobenzene	100	-	-
Chloroform		-	-
Citric acid	10	+	
Cresol			
Cyclohexanone	100		
Cyclohexene	100	+	
Diesel fuel		+	+
Diethylene oxide, THF		+	
Ethyl acetate	100	-	-
Ethyl alcohol	96	+	+
Ethylene chloride	100		
Food oil		+	
Formaldehyde, aqu	40		
Formic acid	10		
Frost protection agent		+	
Fuel , aromatic free		+	+
Glycerin	100	+	
Glycol	100	+	
Heating oil		+	
Heptane	100	+	
Hydrochloric acid	10	+	+
Hydrochloric acid	conc.	o/-	
Hydrofluoric acid	40	o	o/-
Hydrogen peroxide	10	+	o
Hydrogen sulphide			
Isopropyl alcohol	100	+/o	
Linseed oil			
Mercurochrome			
Methyl alcohol	100	+	
Methyl ethyl ketone	100	-	-

Chemical Resistance

GEHR PSU



	conc. (%)	room temperature	60 °C
Methylene chloride	100	-	-
Milk		+	
Mineral oils, aromatic free		+	+
Nitric acid	10	+	+
Nitric acid	50		
Nitrobenzene			
Oxalic acid		+	
Ozone, gas	ca. 0,5 ppm		
Paraffine oil	100		
Perchloroethylene		-	-
Petroleum ether	100		
Petroleum, aromatic free	100		
Phenol, aqu	ca. 9		
Phosphoric acid	50	+	
Potassium hydroxide liquor	50		
Premium Fuel			
Propyl alcohol			
Pyridine			
Silicone oil		+	+
Sodium carbonate, aqu		+	
Sodium chloride, aqu		+	
Sodium hydroxide liquor	15	+	+
Sodium hydroxide liquor	60	+	
Sodium hydrogen sulphite			
Sodium nitrate, aqu			
Sodium thiosulfate			
Sulphuric acid	96	-	-
Tetrahydrofurane	100		
Toluene	100	-	-
Transformer oil		+	
Trichloroethylene	100	-	-
Vinegar, standard	5-10	+	+
Water		+	o
Xylene		-	-

Symbolism for the description of the chemical resistance

- + = resistant (only small changes of the weight, dimensions and properties. According our experiences there is no permanent damage expect).
- o = partly resistant (medium changes of the properties. At longer contact time there are permanent damages recommended e.g. degradation of the macro molecular structure).
- = non resistant (strong and permanent degradation in short contact time e.g. stress cracking).
- = not tested (no tests were done, no recommendations are possible).

The figures indicated here are approximate values. They may be affected by the temperature, operating time, concentration and stress level of the component involved, by mechanical loads, etc., and the user is not released therefore from the obligation of performing checks and trials of his own. The values indicated here have been compiled on the bases of current experiences and findings. Any legally binding guarantee of certain properties, or any suitability for a specific application cannot be inferred from the present data.

Dok.-Nr.	Name	Erstelldatum/Geändert am	Erstellt von	Seite
PSU_engl	Chem-Best	11.12.2007	QM	2 von 2